

Product Description

OBRA molecular sieve 3Å is a crystalline, high porous potassium alumino silicate. Gas, steams and liquids can be adsorbed reversibly or separated selectively due to the special crystal lattice with absolutely uniform, spherical cavities which are connected by channels. The large internal surface of 600 – 700 m²/g results in a stronger bond of adsorption and in polar characteristics of the molecular sieve structure. The pore openings are approx. 3Å across. Molecules bigger than the pore opening of the molecular sieve cannot be adsorbed, smaller can.



**Formela
CAS-No.**


$K_{12}[(AlO_2)_{12} (SiO_2)_{12}] \cdot 12 H_2O$
1318 - 02 - 1

**Physico-chemical
Characteristics**

Adsorption capacity (on dry basis; 40 % RH, 23 °C)	min. 18.5 %
Moisture loss (1h, 550°C)	max. 1.5 %
Bulk density	min. 720 g/l

Particle size

0.7 – 2.0 mm	
> 2.0 mm	max. 10.0 %
< 0.7 mm	max. 10.0 %

	Product Information	
	OBRA molecular sieve 3Å	
Date: 07 / 2019	PI-No.: SIO-12	page 2 of 2
Revision: 01		

Applications	<p>OBRA molecular sieve 3Å is used in various applications, such as the purification of gas, the drying of steam and liquids and the removal of water from air. The reactivation of OBRA molecular sieve 3Å takes place via heating up on 350 – 400 °C or via reduction in pressure. OBRA molecular sieve 3Å has been particularly developed for use in manufacture of insulating glass. Because of pore diameter of approx. 3Å, the molecular sieve does not uptake nitrogen, argon or SF6. Therefore OBRA molecular sieve 3Å is recommended for air-filled as well as for gas-filled insulating glass units.</p>
Packing	<ul style="list-style-type: none"> • Cartons with inserted polyethylene bags á 25 kgs • Steel drums with inserted polyethylene bags á 125 kgs • Big Bags with PE-Inliner á 600 kgs
Handling	<p>OBRA molecular sieve 3Å must always be kept in airtight containers to avoid pre-adsorption with water vapour. Face masks should be used at continual exposure to extensive dusting.</p>
Note	<p>Any details of application possibilities do not free the purchaser from the obligation of performing his own tests on the material supplied by the seller, in order to determine their suitability for the intended processes and purposes. Application, use and processing of the material cannot be controlled by the seller and are thus the sole responsibility of the purchaser</p>